

Producteur :	PHOENIX SERVICES FOS/MER
Granulats :	LAITIER CRISTALLISE 0/60
Pétrographie :	Laitier haut fourneau
Elaboration :	Concassé
Classification :	F8 -Laitier des haut-fourneaux
Utilisation :	Remblais

Classe Granulaire : **0/60**

Norme : NF EN 13242

Partie Contractuelle

	0.063	1	2	3.15	4	10	16	20	31.5	40	50	63	80	LA	MDE	W
Etendue e																
V.S.S.+U														48		
V.S.S.	5.00	26.00	36.00	42.00	44.00	61.00	73.00	80.00	92.00	95.00	98.00	100.00	100.00	45		
V.S.I.	1.00	13.00	15.00	17.00	19.00	34.00	41.00	48.00	63.00	78.00	85.00	92.00	100.00			
V.S.I.-U																

Partie Informatrice

	0.063	1	2	3.15	4	10	16	20	31.5	40	50	63	80	LA	MDE	W
Maximum	1.77	30.13	37.36	42.14	44.53	60.13	73.69	81.01	94.34	97.95	99.50	100.00	100.00	32	32	7.1
Fuseau de fabrication Inconnu	0.92	19.79	24.33	27.33	28.84	39.97	50.80	59.30	76.79	85.42	93.70	99.57	100.00	31	17	2.6
Moyenne Xf	0.92	19.79	24.33	27.33	28.84	39.97	50.80	59.30	76.79	85.42	93.70	99.57	100.00	31	17	2.6
Fuseau de fabrication Inconnu	0.92	19.79	24.33	27.33	28.84	39.97	50.80	59.30	76.79	85.42	93.70	99.57	100.00	31	17	2.6
Minimum	0.00	5.22	6.87	8.24	9.62	18.96	31.32	41.21	62.89	75.95	86.84	95.21	100.00	16	16	1.3
Ecart-type	0.522	7.478	9.192	10.104	10.356	11.908	11.950	11.853	9.605	7.198	4.637	1.298	0.000	4.0	4.0	1.50
Nombre de résultats	14	14	14	14	14	14	14	14	14	14	14	14	14	15	15	14



Caractéristiques du produit

Essais Los Angeles	32%	Essais Micro Deval	16%
--------------------	-----	--------------------	-----

Date et visa du service Qualité :
le 11/06/21

